



CETOL WP 575

For a better wood surface look!





CETOL WP 575



The Cetol WP 575 sanding sealer primarily serves the wood preparation to visually improve the subsequent coating quality. All water-soluble and/or solvent borne Sikkens Joinery paint and varnish systems can be used on the precision ground wood surface pre-treated in this way.

Cetol WP 575 is a water-soluble colorless sanding sealer for parts made from softwood and hardwood. Use Cetol WP 575 for the pre-treatment of the wood in order to produce an even and visually more appealing wood surface. After drying, a wood finish is enough to optimally prepare the surface for further coating with paint

or varnish systems. It is intended for use indoors and outdoors.

In a standard climate, the sanding sealer is dust-dry after 30 minutes, sandable after around four hours and ready for treatment after approx. four to six hours.

AT A GLANCE:

Application:

For dimensionally stable wooden parts

Processing:

Dip and brush coating

Binder type: Special polymer dispersion

Consumption: 40-50 ml/m², depending on applied wet layer

thickness per coat

Colour tone: colorless

Packsize: 5 litres, concentrate

PRODUCT ADVANTAGES:

- More homogeneous wood surface
 - Even absorbtion of the subsequent water-proofing and/or primer
 - Fewer sources of streaks, less wrinkling
- No sanding of the water-proofing necessary thanks to the professional wood pre-treatment and only minimal, slight intermediate sanding necessary after primer or mid coat
- Environmentally friendly and health-conscious for you as the user because the sanding dust is free of biocide

Our technical data sheets and safety data sheets can be found for download at: www.sikkens-joinery.com

Do you have questions about our products? We are here to help:

Akzo Nobel
Wood Finishes and Adhesives
Akzo Nobel Wood Coatings GmbH
Vitalisstrasse 198–226
50827 Cologne · Germany
Tel. +49 221 58 81-0
Fax +49 221 58 81-293
sikkens-holzbau-info@akzonobel.com
www.sikkens-joinery.com

Sikkens is an AkzoNobel brand



9 i fchYW b]WU

euroath@otenet.gr

Ah Ybg Ò|ÉX^} ã^|[~ 232 16341 (\$XO) WÚU Š(ÊAc@) • T^|.: 210 99 59 397 Øæ:.: 210 99 59 398

QåÆ0E^æá. ÂÛā å[•ÊA7ÊÚÈÐĚ4J8 57022 V @••æ4[}ãã T^|.: 2310 796 950 Øæc.: 2310 790 783 info@eurotechnica.gr

H\ YggUcb]]